

Brilliant solution to common technical problems

Miscellaneous :

حلول ساطعة للمشاكل المتكررة

GBcopolymer Hard Tacky

مادة مركزه لمليء الاقمشة لاصقة لكافة الاغراض

Amounts used : 10 – 120 g/l

For back coating of carpet and rugs

300 – 600 g/l **GBcopolymer Hard Tacky**
(you may add **GBcross linker Eco**
According to the desired handle needed .)

Guideline recipes : **Interlining (cotton) ; resilient , stiff finish .**

80 – 120 g/l **GBcross linker Eco**
30-50 g/l **GBsmooth- silicon Resin SR**
30 – 60 g/l **GBcopolymer Hard Tacky**
40 – 60 g/l **GBcopolymer**

Liquor pick-up : approx. 80 %
Dry as usual
Cure : 4 min at 160 °C

Workwear (polyester/cotton)

40 – 60 g/l **GBcross linker Eco**
30 – 50 g/l **GBsmooth- silicon Resin SR**
40 – 80 g/l **GBcopolymer Hard Tacky**
20 – 30 g/ **GBSilicon Excel**

Liquor pick-up : approx 70 %
Dry and cure in one operation at 150 – 170 °C
Actual curing time necessary : approx. 30 s at 170 °C

Table linen and bed sheeting

40 – 80 g/l **GBcopolymer Hard Tacky**
30 – 60 g/l **GBcross linker Eco / GBsmooth- silicon Resin SR**

Liquor pick-up : 70 – 80 %
Dry as usual and calender

ISO 9001:2015

ISO 14001:2015

ISO 45001:2018

Cairo head office: 9,square 1163,El Shaheed Fouad Thabet St.,El Wozara square Sheraton Heliopolis.Cairo- Egypt

Tel: +20222683983, +201228099699 , +202 2268466 E-mail: logistics@gb-chem.net , gbchem@gb-chem.net

Alex. Office: 6, Talat Harb St., Downtown Alexandria, Egypt

Tel.:+203 4819240, +201221148181 , +203 4817565 E-mail: logistics@gb-chem.net , gbchemalex@gb-chem.net

چی بی . کیم

We formulate
German Basic Chemical Products



GBbiopolish enzyme:

An enzyme for especial finishing process & reduce pilling. Act as concentrated acid enzyme for jeans treatments .

انزیم للتجهيز الراقى وتقليل الوبرة ، ويعمل كحامض مركز فى معالجة خامات الجينز .

GBdesizing enzyme:

providing soft touch to the desized materials.& act as economical acid enzyme for jeans treatments.

انزیم لازالة البوش ، ويعمل كحامض اقتصادى فى معالجة خامات الجينز

GBperoxid enzyme:

used for removal of residual hydrogen peroxide after bleaching. The product does not have any negative effect on the textile fibres or dyestuffs

انزیم مزیل للاكسجين ينتج بالطلب .

GBacrylic Retarder :

Versatile retarder & leveling in the dyeing of polyacrylonitrile (acrylic) fibers with cationic dyes.

مبىقى تفاعل وعامل تسويه لاصباغ الاكليرك .

GBcopolymer Hard Tacky : (permanent عجينة لاصق لكافة الاغراض)

ISO 9001:2015

ISO 14001:2015

ISO 45001:2018

Cairo head office: 9,square 1163,El Shaheed Fouad Thabet St.,El Wozara square Sheraton Heliopolis.Cairo- Egypt

Tel: +20222683983, +201228099699 , +202 2268466 E-mail: logistics@gb-chem.net , gbchem@gb-chem.net

Alex. Office: 6, Talat Harb St., Downtown Alexandria, Egypt

Tel.:+203 4819240, +201221148181 , +203 4817565 E-mail: logistics@gb-chem.net , gbchemalex@gb-chem.net

www.gb-chem.net